FINIXA paint processing products

TDS

TECHNICAL DATA SHEET

TECHNICAL SHEET
PLA 03 – Finixa HDPE masking film static in a box-green

Product data

Density:	0,952 g / cm^3
Thickness:	8 µm
Tensile Strength *machine direction*:	≥50 N / mm^2
Tensile Strength *transverse direction*:	≥ 16 N / mm^2
Elongation at break *machine direction*:	> 365 %
Elongation at break *transverse direction*:	> 540
Dart drop:	≥ 6 g/µm
Dimension and design:	as ordered

Indications for storage and application

Storage time:	2 years
Storage temperature:	+ 20°C / ± 10°C
Relative humidity (RH):	30-90%
Storage:	in closed rooms
Exposure to UV-radioation:	to avoid; *not applicable for UV-resistant film
DIMENSION:	380cm x 200m 32 rolls on a pallet

The above information is given in good faith, but the user should assure himself that the performance of the product is sufficient for his application. The quoted values are average and should not be taken as maximum or minimum values for specific purposes. Chemicar Europe cannot be held responsible for product failure unless full testing has been carried out. The client has to decide on the product's suitability for their own applications.

Chemicar Europe nv
Baarbeek 2
2070 Zwijndrecht
België-Belgium

T.: +32 3 234 87 80
F.: +32 3 234 87 89
info@chemicar.eu
www.chemicar.eu