

SOF 19/20/21 – Finixa degreasing cloths

Technical data

Production Method

Spunlace

Composition

Cellulose 55%

Polyester 45%

No Binder

Coulour

SOF 20-21 : Aqua

SOF 19 : White

Weight

± 78 gr/m² (±5%)

Thickness

0.39mm

Tensile Strength

33 lbs (MD)

18 lbs (XD)

Elongation

18% (MD)

78% (XD)

Absorption Time

2 Sec

Absorption Capacity

600%

Areas of Use / Applications



Aerospace



Automotive



Industry



HiTech



Mechanic



Print



Recyclable Energy Recoverable

Packaging Formats



Flat in a box
SOF 19-20



Q/Z Folded
SOF 19-20



Perforated roll
SOF 21

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for our own experimentation.

It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes.

This information may be subject to revision as new knowledge and experience becomes available.

Since we cannot anticipate all variations in actual end-use conditions, Chemicar make no warranties and assume no liability in connection with any use of this information.

This information does not constitute a specification and is only intended to show the typical properties of the product. Product safety information is available on request.

Data in this Technical Data Sheet relates only to the specific materials designated here in and not to use in combination with any other material or process.

The information given here is the best available at time of issue. It is based on our present knowledge but does not constitute a contractual description of product properties.